

CUPA 5

Description, Origin & Production



- **CUPA 5** is a pale grey slate with a riven surface. Split to an average thickness of 5mm and between 7-8 mm for the "Heavy" variant.
- Valdacal Quarry. Puzmazán (Orense), Spain. In operation since 1996.
- 10,000 Tons/year.

Formats & Sizes



Formats Square, Rectangular, Half Moon, Scallop, Schuppen, Spitzort, Spitzwinkel, Rounded & Rustic. Sawed at 90°.

Sizes (cm) Between 20x15 & 60x30, according to formats.

- UK: 60x30 and 50x25. Heavy 30x20, 40x20 and 40x25.
- France: 27x18, 30x20, 32x22, 35x25 (& Scallop), 40x20 Rounded & 40x30 (Scallop).
- Benelux: 30x20, 35x25, 40x22 & 40x25.
- Germany: 20x15 Schuppen, 20x20 Half Moon (UNI), 25x25, 30x30.
- Spain: 30x20, 32x22, 35x25 (& Scallop), 40x25 & 40x30 (Scallop).

* If you are interested in other formats please contact our Customer Service department.



CUPA 5



Technical Specifications

CUPA 5 slates are in compliance with the following specifications:

- European Specifications: EN 12326
- British Standard: BS 680: Part 2
- French Specifications: NF 228-02/03/01
- Belgian Specifications: ATG/H848

WATER ABSORPTION	0.16%
CONTENT IN CARBON NOT CARBONATE	0.24%
CHARACTERISTIC MoR	49
CARBON CONTENT	0.60%
THICKNESS	5 mm, 7-8 mm (Heavy & Scallop)

Grading

All natural slate should be graded into at least 3 thicknesses prior to being placed on the roof. To minimize the effect of any variation in shade, slate should be drawn from at least 2 pallets at time.

As with any natural product, slate is subject to variance, and any slates that are identified at the time of grading as problematic should be cut and used at the eaves or ridge of the roof.

For further information on fixing natural slate please contact your supplier or visit www.cupanaturalslate.co.uk

The images shown may not correspond exactly to the product referenced.



www.cupanaturalslate.co.uk

UK: 45 Moray Place | EDINBURGH EH3 6BQ | Tel. +44 131 22 53 111 | Fax +44 131 22 05 463

Spain: La Medua S/N | 32330 | SOBRADELO DE VALDEORRAS | Ourense | Tel. +34 988 335 410 | Fax +34 988 335 599